

is bestand tegen:

Materiaal	Dichtheid	Temperatuur	Weerstand
Linseed oil	100%	70-90°C	R
Lubricant oil	100%	60-80°C	R
Mineral oil	100%	60-80°C	R
Acetone	25%	20-30°C	R
Acetic acid	10%	40-60°C	R
Acetic acid	25%	30-50°C	R
Acetic acid	50%		NR
Acetic acid	100%		NR
Butyric acid	45%	20-30°C	R
Citrus acid	varias	40-50°C	R
Hydrochlorate acid	conc.		NR
Stearic acid	100%	60-70°C	R
Hydrofluoric acid	30%		NR
Formic acid	10%	20-30°C	R
Phosphoric acid	10%	40-50°C	R
Phosphoric acid	80%	30-40°C	R
Lactic acid	10%	40-60°C	R
Lactic acid	50%	30-40°C	R
Nitric acid	conc.		NR
Oleic acid	100%	60-70°C	R
Sulfuric acid	10%	30-40°C	R
Sulfuric acid	20%	30-40°C	R
Sulfuric acid	50%	20-30°C	R
Sulfuric acid	80%	15-25°C	R
Sulfuric acid	100%		NR
Hydrogen peroxide	various	30-40°C	R
Ethyl alcohol	96%	20-30°C	R
Methyl alcohol	100%	20-30°C	R
Ammonia	1:10	20-30°C	R
Acetic Anhydride	100%		NR
Anhydride ftalic	100%	80-100°C	R
Aniline	100%		NR
Aniline, Hydrochlorate	varias	60-80°C	R
Aniline, Sulphate	varias	60-80°C	R
Benzeno	100%		NR
Sodium bicarbonate	20%	20-30°C	R
Ammonia carbonate	varias	20-30°C	R
Potassium carbonate	10%	20-30°C	R
Sodium carbonate	10%	20-30°C	R
Chloroform	100%		NR
Ammonia chloride	varias	60-80°C	R
Mercury chloride	varias	60-80°C	R
Sodium chloride	varias	60-80°C	R
Zinc chloride	varias	30-40°C	R
Dietilic ether	100%		NR
Etilenglicol	100%	40-60°C	R
Phenol	varias		NR
Flourine	varias		NR
Diesel	100%	50-70°C	R
Gasohol	100%	50-70°C	R
Gasoline	100%	50-70°C	R
Foods fat	100%	70-90°C	R
Mineral fat	100%	70-90°C	R
Sodium hypochloride	conc.		NR
Nafta	100%	70-90°C	R
Caustic soda	20%		NR
Ammonia sulphate	varias	60-80°C	R
Ferric sulphate	varias	60-80°C	R
Ferrous sulphate	varias	60-80°C	R
Sodium sulphate	varias	60-80°C	R
Sodium sulfite	varias	60-80°C	R
Zinc sulphate	varias	50-60°C	R
Sodium sulfide	varias	50-60°C	R
Trietanolamine	varias	20-30°C	R
Trietilamine	100%		NR